TABLE 5

Ex. No.	Dye I* n	R 1	Dye (7) from Ex. 49	Dye II X	R^2	R^3=R^4	R^5	Dye III X^1	X^2	R^7=R^8	R^6
49	1	H	from Ex. 49	Cl	CH_3	$CH_2CH=CH_2$	CH_3	Cl	NO_2	C_2H_5	CH_3
50	1	H	from Ex. 49	Cl	C_2H_5	C_2H_5	C_2H_5	Cl	NO_2	C_2H_5	CH_3
51	1	H	from Ex. 49	Br	CH_3	C_2H_5	CH_3	Br	NO_2	C_2H_5	CH_3
52	1	H	from Ex. 49	Cl	CH_3	C_2H_5	CH_3	Br	NO_2	C_2H_5	CH_3
53	1	H	from Ex. 49	Br	CH_3	$CH_2CH=CH_2$	CH_3	Br	NO_2	C_2H_5	CH_3

*Ring A not further substituted

What is claimed is:

1. A mixture comprising at least one compound of the formula (I)



(I)

where

R^1 is hydrogen, C_1–C_4-alkyl, halogen, or C_1–C_4-alkoxy,

n is 1 or 2, and the

ring A is optionally substituted,

and at least one compound of the formula (II)



(II)

where

X is halogen, or CN,

R^2 and R^5 are independently hydrogen or C_1–C_4-alkyl, and

R^3 and R^4 are independently hydrogen, optionally substituted C_1–C_4-alkyl or C_2–C_4-alkenyl.

2. The mixture of claim 1, comprising at least one compound of the formula (I) where the ring A does not bear any further substituents.

3. The mixture of claim 1, comprising at least one compound of the formula (I) where R^1 is hydrogen or C_1–C_4-alkyl.

4. The mixture of claim 1, comprising at least one compound of the formula (I), where n is 1, R^1 is hydrogen or methyl and the ring A is not further substituted.

5. The mixture of claim 1, comprising compounds of the formula (II) where X is halogen.

6. The mixture of claim 1, comprising compounds of the formula (II) where

R^3 and R^4 are independently hydrogen, C_2–C_4-alkenyl, unsubstituted C_1–C_4-alkyl or ROCO—, NC— and/or ROOC-substituted C_1–C_4-alkyl, R being hydrogen or C_1–C_4-alkyl.

7. The mixture of claim 1, comprising a compound of the formula (III), (IV) and/or (V)



(III)



(IV)

and/or

-continued

(V)



where

X^1 is halogen or CN,

X^2 is halogen, hydrogen, NO_2 or CN,

R^6 is C_1–C_4-alkyl,

R^7 and R^8 are independently hydrogen, unsubstituted or HO—, NC—, ROCO—, H_5C_6OCO—, (C_1–C_4-alkyl)OOCO—, ROOC—, H_5C_6O—, H_5C_6— and/or C_1–C_4-alkoxy-substituted C_1–C_4-alkyl and/or C_2–C_4-alkenyl, R being hydrogen or C_1–C_4-alkyl,

Y^1 and Y^2 are independently hydrogen or halogen,

R^9 and R^{10} are independently hydrogen, unsubstituted or HO—, NC—, ROCO—, H_5C_6OCO— and/or C_1–C_4-alkoxy-substituted C_1–C_4-alkyl, R being as defined above, or C_2–C_4-alkenyl,

R^{11} is C_1–C_4-alkyl, and

R^{12} is hydrogen, C_1–C_4-alkyl or C_1–C_4-alkoxy.

8. The mixtures of claim **1**, comprising 1 to 99% by weight, especially 1 to 80% by weight, of at least one compound of the formula (I) and 1 to 99% by weight, especially 20 to 99% by weight, of at least one compound of the formula (II), based on total amount of dye.

9. A dye preparation comprising

10 to 60% by weight of dye mixture according to claim **1**, and

40 to 90% by weight of dispersant.

10. A process for producing the dye preparation of claim **8**, in which the individual dyes of the dye mixture of claim **1** are ground in water in the presence of a dispersant, then mixed and optionally dried or in which the dye mixture of claim **1** is ground in water in the presence of a dispersant and optionally dried.

11. A method for dyeing and printing hydrophobic synthetic materials or for mass coloration of hydrophobic synthetic materials in which the dye mixture of claim **1** is used.

12. The hydrophobic synthetic material dyed or printed with the dye mixture of claim **1**.

* * * * *